

TECHNICAL DATA

SNOWBULK

Parameter	Value	Tolerance	Comment
Basis Weight	55 to 90 g/m ²	-2/+3 g/m ²	As specified by Customer
Bulk / Volume	1.6 / 16 to 2.4 / 24		55 gsm starts at Bulk 1.8
Caliper	99 to 180 micron	+/- 4 micron	180 micron maximum
Brightness	70 iso	+/- 0.75	
Shade	7.5 (Cream) or 4 (Blue/White)	+/- 0.5	Cream or Blue White
Opacity	88 to 96	+/- 1	Dependant on grammage/caliper
Moisture	8%	+/- 0.5	
Tear	240 to 450 Nm	+/- 0.4	
Tensile	2.40 to 4.50 kN/m	+/- 0.4	
Main furnish	90% mechanical groundwood (Spruce)		
Secondary furnish	10% Avg. sulfat cellulose		
Wrapping	Kraft wrappers		2 layers
Cores	76mm strawboard		
Joins	Maximum 2 joins per reel		Marked by red line on reel
Reel Diameter	1000mm or 1150mm		As specified by customer
Accreditation	FSC and PEFC	Mix Credit NC-COC-016937	FSC Paper on request

All paper supplied according to the General Trade Rules for the supply of paper and paperboard.

Should Technical Data be required for a specific grammage/caliper combination these can be provided upon request.