



**Hellefoss
Paper AS**

TECHNICAL DATA

SUPER SNOWBRIGHT

Parameter	Value	Tolerance	Comment
Basis Weight	60 to 90 g/m ²	-2/+3 g/m ²	As specified by Customer
Bulk / Volume	1.6 / 16 to 2.3 / 23		As specified by Customer
Caliper	96 to 180 micron	+/- 4 micron	180 micron maximum
Brightness	80 iso	+/- 0.75	
Shade	1 (Blue White) or 8 (Cream)	+/- 0.5	As specified by customer
Opacity	84 to 94	+/- 1	Dependant on grammage/caliper
Moisture	8%	+/- 0.5	
Tear	300 to 450 Nm	+/- 0.4	
Tensile	300 to 4.50 kN/m	+/- 0.4	
Main furnish	80 to 85% mechanical groundwood		Produced from Norwegian Spruce
Secondary furnish	10% Avg. cellulose (Spruce)		
Wrapping	Kraft wrappers		2 layers
Cores	76 mm strawboard		
Joins	Maimum 2 joins per reel		Marked by red line on reel
Reel Diameter	1000 mm or 1150 mm		As specified by customer
Accreditation	FSC	Volume Credit	FSC Paper on request

All paper supplied according to the General Trade Rules for the supply of paper and paperboard.

Should Technical Data be required for a specific grammage/caliper combination these can be provided upon request.